

AMENDMENTS TO THE CLAIMS:

Please replace the claims with the claims provided in the listing below wherein status, amendments, additions and cancellations are indicated.

1. (Currently amended) A fluorescent material, comprising:
an [[An]] alkaline earth metal aluminate fluorescence-type phosphor of a
type exhibiting fluorescence, said alkaline earth metal aluminate phosphor
comprising:

- bivalent europium as an activator;
- barium and/or strontium;
- magnesium;
- aluminum; and
- at least one element (e) selected from the group consisting of
indium, tungsten, niobium, bismuth, molybdenum, tantalum, thallium and
lead.

2. (Currently amended) The fluorescent material ~~alkaline earth metal~~
~~aluminate fluorescence-type phosphor~~ according to Claim 1, which is obtained by
a process comprising:

a step (1-1) of firing, in a reducing atmosphere, a mixture of precursor
compounds of barium and/or strontium (a), magnesium (b), aluminum (c),

europium (d) and at least one element (e) selected from the group consisting of indium, tungsten, niobium, bismuth, molybdenum, tantalum, thallium and lead, respectively[.]; and

a step (1-2) of firing, in an oxidizing atmosphere, the fired product obtained in the step (1-1).

3. (Currently amended) The fluorescent material ~~alkaline earth metal aluminate fluorescence-type phosphor~~ according to Claim 1, which is obtained by a process comprising:

a step (2-1) of mixing a fired product (A) with a compound (B), said fired product (A) comprising barium and/or strontium (a), magnesium (b), aluminum (c) and europium (d), said compound (B) comprising at least one compound selected from the group consisting of indium compounds, tungsten compounds, niobium compounds, bismuth compounds, molybdenum compounds, tantalum compounds, thallium compounds and lead compounds; and

a step (2-2) of firing, in an oxidizing atmosphere, the mixture obtained in the step (2-1) or a fired product of the mixture obtained in the step (2-1), said step (2-2) being preceded, at least once, by firing in a reducing atmosphere.

4. (Currently amended) The fluorescent material ~~alkaline earth metal aluminate fluorescence-type phosphor~~ according to any one of Claims 1 to 3,

wherein the content of the at least one element (e) selected from the group consisting of indium, tungsten, niobium, bismuth, molybdenum, tantalum, thallium and lead is within a range of 0.0001 to 0.01 mole per mole of the aluminum element.

5. (Currently amended) The fluorescent material ~~alkaline earth metal aluminate fluorescence-type phosphor~~ according to any one of Claims 1 to 3, wherein the alkaline earth metal aluminate phosphor containing bivalent europium as an activator comprises a compound represented by the following general formula (1):



wherein X satisfies a relationship of $0 \leq X \leq 0.3$ and Y satisfies a relationship of $0 < Y \leq 0.2$.

6. (Currently amended) The fluorescent material ~~alkaline earth metal aluminate fluorescence-type phosphor~~ according to any one of Claims 1 to 3, which has a powder whiteness of not lower than 85 as expressed in terms of W value.

7. (Currently amended) A method of producing the alkaline earth metal aluminate ~~fluorescence-type phosphors~~ phosphor according to Claim 1, comprising:

a step (1-1) of firing, in a reducing atmosphere, a mixture of precursor compounds of barium and/or strontium (a), magnesium (b), aluminum (c), europium (d) and at least one element (e) selected from the group consisting of indium, tungsten, niobium, bismuth, molybdenum, tantalum, thallium and lead, respectively, or a fired product of said mixture.

8. (Currently amended) The method ~~of producing alkaline earth metal aluminate fluorescence-type phosphors~~ according to Claim 7, further comprising: a step (1-2) of firing, in an oxidizing atmosphere, the fired product obtained in the step (1-1) of firing in a reducing atmosphere.

9. (Currently amended) The method ~~of producing alkaline earth metal aluminate fluorescence-type phosphors~~ according to Claim 7 or 8, further comprising:

a step (1-3) of firing in an oxidizing atmosphere in advance of the step (1-1) of firing in a reducing atmosphere.

10. (Currently amended) A method ~~of producing alkaline earth metal aluminate fluorescence-type phosphors~~ according to Claim 1 or 3, comprising:

a step (2-1) of mixing a fired product (A) with a compound (B), said fired product (A) comprising barium and/or strontium (a), magnesium (b), aluminum (c) and europium (d), said compound (B) comprising at least one compound selected from the group consisting of indium compounds, tungsten compounds, niobium compounds, bismuth compounds, molybdenum compounds, tantalum compounds, thallium compounds and lead compounds; and

a step (2-2) of firing, in an oxidizing atmosphere, the mixture obtained in the step (2-1) or a fired product of the mixture obtained in the step (2-1), said step (2-2) being preceded, at least once, by firing in a reducing atmosphere.

11. (Currently Amended) The method ~~of producing alkaline earth metal aluminate fluorescence-type phosphors~~ according to Claim 10, wherein said fired product (A) further comprises at least one element (e) selected from the group consisting of indium, tungsten, niobium, bismuth, molybdenum, tantalum, thallium and lead.

12. (Currently amended) The method ~~of producing alkaline earth metal aluminate fluorescence-type phosphors~~ according to Claim 10, wherein said firing in a reducing atmosphere comprises firing the mixture obtained in the step (2-1).

13. (Currently amended) The method of ~~producing alkaline earth metal aluminate fluorescence-type phosphors~~ according to Claim 10, wherein said firing in a reducing atmosphere comprises firing product (A) for producing the fired product (A) comprising barium and/or strontium (a), magnesium (b), aluminum (c) and europium (d).

14. (New) The fluorescent material according to Claim 1, wherein the alkaline earth metal aluminate phosphor exhibits an emission decay of sufficiently short duration so as to be suitable for use in a plasma display panel.

15. (New) A fluorescent material, comprising:
an alkaline earth metal aluminate phosphor being of a type exhibiting fluorescence, said alkaline earth metal aluminate phosphor comprising bivalent europium as an activator, barium and/or strontium, magnesium, aluminum and at least one element (e) selected from the group consisting of indium, tungsten, niobium, bismuth, molybdenum, tantalum, thallium and lead, a content of the at least one element (e) being within a range of 0.0001 to 0.01 mole per mole of said aluminum; and

said alkaline earth metal aluminate fluorescence-type phosphor being comprised of a compound represented by the following general formula (1):



wherein X satisfies a relationship of $0 \leq X \leq 0.3$ and Y satisfies a relationship of $0 < Y \leq 0.2$.